

(11) **EP 1 033 767 A1**

(12) **EUROPEAN PATENT APPLICATION**
published in accordance with Art. 158(3) EPC

(43) Date of publication:
06.09.2000 Bulletin 2000/36

(51) Int. Cl.⁷: **H01M 4/58**

(21) Application number: **99943403.8**

(86) International application number:
PCT/JP99/05093

(22) Date of filing: **17.09.1999**

(87) International publication number:
WO 00/17949 (30.03.2000 Gazette 2000/13)

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE

(30) Priority: **18.09.1998 JP 28208798**
26.02.1999 JP 5047199

(71) Applicant:
CANON KABUSHIKI KAISHA
Ohta-ku Tokyo 146-8501 (JP)

(72) Inventors:
• **KAWAKAMI, Solchiro**
Ohta-ku Tokyo 146 (JP)
• **ASAO, Masaya**
Ohta-ku Tokyo 146 (JP)

(74) Representative: **Weser, Wolfgang**
Weser & Kollegen,
Patentanwälte,
Radeckestrasse 43
81245 München (DE)


(54) **ELECTRODE MATERIAL FOR NEGATIVE POLE OF LITHIUM SECONDARY CELL,
ELECTRODE STRUCTURE USING SAID ELECTRODE MATERIAL, LITHIUM SECONDARY
CELL USING SAID ELECTRODE STRUCTURE, AND METHOD FOR MANUFACTURING SAID
ELECTRODE STRUCTURE AND SAID LITHIUM SECONDARY CELL**

(57) An electrode material for an anode of a rechargeable lithium battery, containing a particulate comprising an amorphous $M \cdot A \cdot X$ alloy with a substantially non-stoichiometric ratio composition. [For said formula $M \cdot A \cdot X$, M indicates at least one kind of an element selected from a group consisting of Si, Ge, and Mg, A indicates at least one kind of an element selected from a group consisting of transition metal elements, X indicates at least one kind of an element selected from a group consisting of O, F, N, Ba, Sr, Ca, La, Ce, C, P, S, Se, Te, B, Bi, Sb, Al, In, and Zn, where the element X is

not always necessary to be contained. The content of the constituent element M of the amorphous $M \cdot A \cdot X$ alloy is $M/(M + A + X) = 20$ to 80 atomic% .]

An electrode structural body for a rechargeable lithium battery, comprising said electrode material for an anode and a collector comprising a material incapable of being alloyed with lithium in electrochemical reaction, and a rechargeable lithium battery having an anode comprising said electrode structural body.

FIG.1(b)



EP 1 033 767 A1